



TECHNICAL SHEET

(according to the standard UNI EN ISO 14465)

ARTICLE:	VG-4354 TF/ACC STRETCH
COMPOSITION:	95%PL 5%EA
WEIGHT G/M LIN.:	850
REPEAT(WARP/WEFT):	NO
METERS PER ROLL:	25
WIDHT CM:	140

REGULAR CARE AND LEGAL GUARANTEE:

Regular cleaning is important to keep the upholstery fabric looking its best and to extend its life. The guarantee is subject to the correct use of the fabric and its maintenance.

It is usually recommended that upholstered furniture with normal commercial use should be cleaned 2-3 times a year.

Upholsteries in private households usually need less frequent cleaning. In order to ensure satisfying cleaning results, we recommend to contact a professional cleaning institute.

Please follow the maintenance instructions of the technical data sheet.

- Abrasion Resistance - Martindale UNI EN ISO 12947-2 + EN 14465, appendice A	Color degradation after 3000 giri: 4/5 Color degradation after 6000 giri: 4 END POINT (rubs): > 50,000
Pilling resistance by the modified martindale method UNI EN ISO 12945-2	Degradation average photographic scale 1/5 : 3/4 At 2000 rubs: 4
Colour fastness to light UNI EN ISO 105-B02	Blue scale 1/8 result: 4/5
Colour fastness to rubbing UNI EN ISO 105-X12	Grey scale 1/5 dry: 3/4 wet: 3/4
Dimensional change after washing UNI EN ISO 6330	Narrowing (weft): Shortening (warp):
Dimensional change after dry cleaning UNI EN ISO 3175	Narrowing (weft): <= +/-3% Shortening (warp): <= +/-3%
Resistance to yarn Slippage at stitched seams UNI EN ISO 13937-3 (din 14465)	Weft mm < 6 warp mm < 6
Fire Resistance	TO BE TESTED
Environmental benefits	<ul style="list-style-type: none"> - No use of AZO dyes, which may split off carcinogenic acrylic amines. - No use of dyes containing heavy metals/complies with ETAD norm. - No use of brominated flame retardants. - Compiles with REACH regulation.
Sustainability	ECO-PATH (available on request)
Available teflon treatment	(on request)
Type of finish used	EXCLUSIVE FOR STRETCH ITEMS
Tariff code	6001100010
Raw Material & Weaving	Made in Italy





LANARTEX S.r.l.

Via I Maggio, 27

59013 Oste - Montemurlo (PO)

Tel.: 0574-071701 Fax: 0574-899903

E-mail: labo@lanartex.it

www.lanartex.it



LAB N° 0572 L

REPORT NR
REPORT DATE

230006794-001
18/10/2023

TEST LIST

TEST	METHOD	ACCREDIA
Abrasion resistance <i>Resistenza all' abrasione</i>	UNI EN ISO 12947-1:2000 + UNI EN ISO 12947-2:2017	
Analysis of fabric propensity to surface Pilling, Fuzzing or Matting. <i>Analisi della tendenza alla formazione di Pilling, Fuzzing o Matting.</i>	UNI EN ISO 12945-2:2021 + UNI EN ISO 12945-4:2021	
Resistance to Slippage of Yarns <i>Resistenza allo scorrimento delle cuciture</i>	UNI EN ISO 13936-2:2004	

(*) = Tests and analytes marked with asterisk are not accredited ACCREDIA. The content of the present document refers **exclusively to the submitted samples** and not to the batch that they want to represent. This report is made solely on the basis of materials supplied by the customer. This test report cannot be reproduced in part without written permission of LANARTEX. The sample description content is under the full responsibility of the customer and not of the laboratory. Except when specifically stated, **the results apply to the sample as received**. For any further information, please read the General Sales Condition on the Lanartex website.



LANARTEX S.r.l.

Via I Maggio, 27

59013 Oste - Montemurlo (PO)

Tel.: 0574-071701 Fax: 0574-899903

E-mail: labo@lanartex.it

www.lanartex.it



LAB N° 0572 L

REPORT NR
REPORT DATE

230006794-001
18/10/2023

RESULTS

	M.U.	RESULT
UNI EN ISO 12947-1:2000 + UNI EN ISO 12947-2:2017		
Abrasion resistance		
<i>Resistenza all' abrasione</i>		
Sample type detail		
<i>Dettaglio tipologia campione</i>		
Applied load		12
<i>Carico applicato</i>		kPa
Abrading fabric		Standard wool
<i>Mezzo abrasente</i>		Lana standard
Type of End point		> 50000 rubs as agreed with the customer
<i>Tipologia di End point</i>		> 50000 sfregamenti come richiesto dal committente
Pilling remove		None
<i>Rimozione pilling</i>		Non avvenuta
Number of specimens		3
<i>Numero di provini</i>		Nr
Change of Tone at End Point		2
<i>Cambio di Tono a End Point</i>		Grado
Result prior to the End Point - Specimen 1		> 50000
<i>Risultato antecedente all' End Point - Provino 1</i>		Sfreg.
Result prior to the End Point - Specimen 2		> 50000
<i>Risultato antecedente all' End Point - Provino 2</i>		Sfreg.
Result prior to the End Point - Specimen 3		> 50000
<i>Risultato antecedente all' End Point - Provino 3</i>		Sfreg.
Significant result		> 50000
<i>Risultato significativo</i>		Sfreg.

NOTES

The specimens have been acclimatized in atmosphere to 20±2°C and 65±4%RH in compliance with norm UNI EN ISO 139; Instrument: Martindale; CT: it shows the number of cycles at which a change in the aspect is observed and evaluated on the Grey scale for colour change.

I campioni da testare sono stati ambientati in ambiente a 20±2°C e 65±4%UR conformemente alla norma UNI EN ISO 139; Strumento: Martindale; CT: indica il numero di cicli al quale si osserva un cambiamento di aspetto valutato con la scala dei grigi (cambiamento di tono).

	M.U.	RESULT
UNI EN ISO 12945-2:2021 + UNI EN ISO 12945-4:2021		
Analysis of fabric propensity to surface Pilling, Fuzzing or Matting.		
<i>Analisi della tendenza alla formazione di Pilling, Fuzzing o Matting.</i>		
Number of specimens		
<i>Numero di provette</i>		3
Abrading fabric		Standard wool
<i>Mezzo abrasente</i>		Lana standard

(*) = Tests and analytes marked with asterisk are not accredited ACCREDIA. The content of the present document refers **exclusively to the submitted samples** and not to the batch that they want to represent. This report is made solely on the basis of materials supplied by the customer. This test report cannot be reproduced in part without written permission of LANARTEX. The sample description content is under the full responsibility of the customer and not of the laboratory. Except when specifically stated, **the results apply to the sample as received**. For any further information, please read the General Sales Condition on the Lanartex website.

**LANARTEX S.r.l.**

Via I Maggio, 27
59013 Oste - Montemurlo (PO)
Tel.: 0574-071701 Fax: 0574-899903
E-mail: labo@lanartex.it
www.lanartex.it



LAB N° 0572 L

REPORT NR
REPORT DATE

230006794-001
18/10/2023

Applied load		415±2
<i>Carico applicato</i>	g	
Pilling - Average assessment at 500 rubs		4
<i>Pilling - Valutazione a 500 sfregamenti media</i>	Grado	
Fuzzing - Average assessment at 500 rubs		3-4
<i>Fuzzing - Valutazione a 500 sfregamenti media</i>	Grado	
Matting - Average assessment at 500 rubs		3-4
<i>Matting - Valutazione a 500 sfregamenti media</i>	Grado	
Pilling - Average assessment at 1.000 rubs		4
<i>Pilling - Valutazione a 1.000 sfregamenti media</i>	Grado	
Fuzzing - Average assessment at 1.000 rubs		3-4
<i>Fuzzing - Valutazione a 1.000 sfregamenti media</i>	Grado	
Matting - Average assessment at 1.000 rubs		3
<i>Matting - Valutazione a 1.000 sfregamenti media</i>	Grado	
Pilling - Average assessment at 2.000 rubs		4
<i>Pilling - Valutazione a 2.000 sfregamenti media</i>	Grado	
Fuzzing - Average assessment at 2.000 rubs		3-4
<i>Fuzzing - Valutazione a 2.000 sfregamenti media</i>	Grado	
Matting - Average assessment at 2.000 rubs		3
<i>Matting - Valutazione a 2.000 sfregamenti media</i>	Grado	
Pilling - Average assessment at 5.000 rubs		4
<i>Pilling - Valutazione a 5.000 sfregamenti media</i>	Grado	
Fuzzing - Average assessment at 5.000 rubs		3-4
<i>Fuzzing - Valutazione a 5.000 sfregamenti media</i>	Grado	
Matting - Average assessment at 5.000 rubs		4
<i>Matting - Valutazione a 5.000 sfregamenti media</i>	Grado	
Test finished at (according to the customer)		5000
<i>Test concluso a (in accordo con il cliente)</i>	Sfreg.	

NOTES

The specimens have been conditioned in atmosphere to 20±2°C and 65±4%RH in compliance with norm UNI EN ISO 139; Number of observers: 2. Assessment in compliance with ISO 12945-4 standard.

I campioni da testare sono stati condizionati in ambiente a 20±2°C e 65±4%UR conformemente alla norma UNI EN ISO 139; Numero di osservatori: 2. Valutazione eseguita in conformità alla normativa ISO 12945-4.

	M.U.	RESULT
UNI EN ISO 13936-2:2004		
Resistance to Slippage of Yarns		
<i>Resistenza allo scorrimento delle cuciture</i>		
Prefixed load		180
<i>Forza di trazione impostata</i>	N	
Wales slippage - Number of specimens		5
<i>Scorrimento di Fila - Numero di provette</i>	Nr	
Wales slippage - Seam slippage		1.0
<i>Scorrimento di Fila - Scorrimento cuciture</i>	mm	

(*) = Tests and analytes marked with asterisk are not accredited ACCREDIA. The content of the present document refers **exclusively to the submitted samples** and not to the batch that they want to represent. This report is made solely on the basis of materials supplied by the customer. This test report cannot be reproduced in part without written permission of LANARTEX. The sample description content is under the full responsibility of the customer and not of the laboratory. Except when specifically stated, **the results apply to the sample as received**. For any further information, please read the General Sales Condition on the Lanartex website.



LANARTEX S.r.l.

Via I Maggio, 27

59013 Oste - Montemurlo (PO)

Tel.: 0574-071701 Fax: 0574-899903

E-mail: labo@lanartex.it

www.lanartex.it



LAB N° 0572 L

REPORT NR
REPORT DATE

230006794-001
18/10/2023

Courses slippage - Number of specimens

Scorrimento di Ranghi - Numero di provette

Nr

5

Courses slippage - Seam slippage

Scorrimento di Ranghi - Scorrimento cuciture

mm

1.1

NOTES

The specimens have been acclimatized in atmosphere to $20 \pm 2^\circ\text{C}$ and $65 \pm 4\%\text{RH}$ in compliance with norm UNI EN ISO 139; Apparatus: Dynamometer CRE - Sewing Machine: Juki Mod. CP-180; Seam type: 301 SS. Sampling: according to Annex B of the standard, except other indication. The test was performed in derogation from the standard on a knitted fabric at the request of the customer, is therefore indicative. The laboratory declines all responsibility in this regard.

I campioni da testare sono stati ambientati in ambiente a $20 \pm 2^\circ\text{C}$ e $65 \pm 4\%\text{UR}$ conformemente alla norma UNI EN ISO 139; Apparecchiatura di prova: Dinamometro CRE - Macchina per cucire: Juki Mod. CP-180; Tipo cucitura: 301 SS. Campionamento: secondo norma in accordo con l'Annex B, salvo diverse indicazioni. La prova è stata condotta in deroga alla normativa su di un tessuto a maglia su richiesta del committente, è pertanto indicativa. Il laboratorio declina ogni responsabilità in merito.

END OF REPORT



egoitaliano[®]
LIVING YOUR WAY

LAMBY
Categoria
C

Si tratta di una pelliccia di poliestere, voluminosa e riccia, ha lo stesso look di una pelliccia agnellata, tuttavia la sua mano è assolutamente morbida e setosa.

è un tessuto Stretch, con una coloritura varia e intensa. La sua manutenzione è estremamente semplice, trattandosi di un poliestere.

It is a polyester fur, voluminous and curly, it has the same look as a lambskin fur, yet its hand is absolutely soft and silky. It is a stretch fabric, with a varied and intense coloring. Its maintenance is extremely easy, as it is a polyester.